

Mold-Tech A Finishes

NO.	Texture Depth (Inch)	Texture Depth (mm)	Minimun Draft (°)
MT-11000	0.0004	0.01016	1°
MT-11010	0.001	0.0254	1.5°
MT-11020	0.0015	0.0381	2.5°
MT-11030	0.002	0.0508	3°
MT-11040	0.003	0.0762	4.5°
MT-11050	0.0045	0.1143	6.5°
MT-11060	0.003	0.0762	4.5°
MT-11070	0.003	0.0762	4.5°
MT-11080	0.002	0.0508	3°
MT-11090	0.0035	0.0889	5.5°
MT-11100	0.006	0.1524	9°
MT-11110	0.0025	0.0635	4°
MT-11120	0.002	0.0508	3°
MT-11130	0.0025	0.0635	4°
MT-11140	0.0025	0.0635	4°
MT-11150	0.00275	0.06985	4°
MT-11160	0.004	0.1016	6°

Mold-Tech B Finishes

NO.	Texture Depth (Inch)	Texture Depth (mm)	Minimum Draft (°)
MT-11200	0.003	0.0762	4.5°
MT-11205	0.0025	0.0635	4°
MT-11210	0.0035	0.0889	5.5°
MT-11215	0.0045	0.1143	6.5°
MT-11220	0.005	0.127	7.5°
MT-11225	0.0045	0.1143	6.5°
MT-11230	0.0025	0.0635	4°
MT-11235	0.004	0.1016	6°
MT-11240	0.0015	0.0381	2.5°
MT-11245	0.002	0.0508	3°
MT-11250	0.0025	0.0635	4°
MT-11255	0.002	0.0508	3°
MT-11260	0.004	0.1016	6°
MT-11265	0.005	0.127	7°
MT-11270	0.004	0.1016	6°
MT-11275	0.0035	0.0889	5°
MT-11280	0.0055	0.1397	8°

Mold-Tech C Finishes

NO.	Texture Depth (Inch)	Texture Depth (mm)	Minimun Draft (°)
MT-11300	0.0025	0.0635	3.5°
MT-11305	0.005	0.127	7.5°
MT-11310	0.005	0.127	7.5°
MT-11315	0.001	0.0254	1.5°
MT-11320	0.0025	0.0635	4°
MT-11325	0.003	0.0762	4.5°
MT-11330	0.002	0.0508	3°
MT-11335	0.002	0.0508	3°
MT-11340	0.003	0.0762	4.5°
MT-11345	0.003	0.0762	4.5°
MT-11350	0.0035	0.0889	5.5°
MT-11355	0.0025	0.0635	4°
MT-11360	0.0035	0.0889	5.5°
MT-11365	0.0045	0.1143	7°
MT-11370	0.004	0.1016	6°
MT-11375	0.004	0.1016	6°
MT-11380	0.004	0.1016	6°

Mold-Tech D Finishes

NO.	Texture Depth (Inch)	Texture Depth (mm)	Minimun Draft (°)
MT-11400	0.002	0.0508	3°
MT-11405	0.0025	0.0635	4°
MT-11410	0.0035	0.0889	5.5°
MT-11415	0.002	0.0508	3°
MT-11420	0.0025	0.0635	4°
MT-11425	0.0035	0.0889	5.5°
MT-11430	0.007	0.1778	10°
MT-11435	0.01	0.254	15°
MT-11440	0.0005	0.0127	1.5°
MT-11445	0.0015	0.0381	2.5°
MT-11450	0.0025	0.0635	4°
MT-11455	0.003	0.0762	4.5°
MT-11460	0.0035	0.0889	5.5°
MT-11465	0.005	0.127	7.5°
MT-11470	0.002	0.0508	3°
MT-11475	0.002	0.0508	3°
MT-11480	0.003	0.0762	4.5°